



# MACHINING CONDITIONS

APKT 100304 PDTR LT 30

M0002920

Material Group	SAPPHIRE TOOLS	Material Example	Hardness	D.O.C		Feed		Vc		Advised D.O.C	Advised Feed	Advised Vc	
				min[mm]	max[mm]	min[mm/t]	max [mm/t]	min [m/min]	max [m/min]				
				[mm]	[mm/t]	[m/min]	[m/min]	[mm]	[mm/t]				
Steel	Non Alloyed	1	C35, Ck45, 1020, 1045, 1060, 28Mn6	125 HB	0.5	9	0.11	0.2	190	330	2	0.14	250
				190 HB	0.5	9	0.11	0.2	190	300	2	0.14	220
				250 HB	0.5	9	0.11	0.2	190	250	2	0.14	200
	Low Alloyed	2	42CrMo4, St50, Ck60, 4140, 4340, 100Cr6	230 HB	0.5	9	0.09	0.16	150	210	2	0.12	180
				280 HB	0.5	9	0.09	0.14	130	190	2	0.11	150
				180 HB	0.5	9	0.09	0.16	150	240	2	0.12	200
	High Alloyed	3	X40CrMoV5, H13, M42, D3, S6-5-2, 12Ni19	350 HB	0.5	9	0.09	0.14	130	170	2	0.11	140
				220 HB	0.5	6.4	0.07	0.14	90	150	1.5	0.11	130
				280 HB	0.5	6.4	0.07	0.14	90	130	1.5	0.11	120
				320 HB	0.5	6.4	0.07	0.11	60	110	1.5	0.1	100
Stainless Steel	Austentic	4	304, 316, X5CrNi18-9	350 HB	0.5	6.4	0.07	0.11	60	90	1.5	0.1	80
				180 HB	0.5	9	0.09	0.16	190	250	2	0.12	220
	Duplex	5	X2CrNiN23-4, S31500	240 HB	0.5	9	0.07	0.14	160	210	2	0.12	190
				290 HB	0.5	6.4	0.07	0.11	70	130	1.5	0.1	100
	Ferritic & Martensitic	6	410, X6Cr17, 17-4 PH, 430	310 HB	0.5	6.4	0.07	0.11	70	120	1.5	0.1	90
				200 HB	0.5	9	0.09	0.16	150	210	2	0.12	190
Cast Iron	Grey	7	GG20, GG40, EN-GJL-250, N030B	42 HRc	0.5	6.4	0.09	0.12	90	150	1.5	0.1	130
				150 HB	0.5	9	0.11	0.2	150	240	2	0.14	200
				200 HB	0.5	9	0.11	0.2	150	220	2	0.14	180
	Malleable & Nodular	8	GGG40, GGG70, 50005	250 HB	0.5	9	0.11	0.2	150	190	2	0.14	160
				150 HB	0.5	9	0.09	0.17	100	200	2	0.12	180
				200 HB	0.5	9	0.09	0.17	100	180	2	0.12	150
NiTi Alloy	Fe, Ni & Co Based	9	Incoloy 800	240 HB	0.5	6.4	0.07	0.11	30	50	1.5	0.1	32
			Inconel 700	250 HB	0.5	6.4	0.07	0.11	30	50	1.5	0.1	30
			Stellite 21	350 HB	0.5	6.4	0.07	0.11	30	50	1.5	0.1	30
	Ti Based	10	T40	-	0.5	6.4	0.07	0.11	30	60	1.5	0.1	40
			TiAl6V4	-	0.5	6.4	0.07	0.12	40	70	1.5	0.11	55
Hardened Materials	Steel Chilled Cast Iron White Cast Iron	11	G-X300CrMo15	55 HRc	0.5	1	0.06	0.09	30	60	0.5	0.07	40
			Ni-Hard 2	400 HB	0.5	2.6	0.06	0.11	40	80	0.8	0.09	50
			X100CrMo13, 440C, G-X260NiCr42	45 HRc	0.5	3.2	0.06	0.11	40	80	1	0.09	60
				50 HRc	0.5	1.9	0.06	0.1	40	70	0.8	0.08	55
				55 HRc	0.5	1	0.06	0.09	40	60	0.5	0.07	50
Aluminium	Al (>8%Si)	12	AlSi12	130 HB	0.5	9	0.11	0.2	200	400	2	0.16	280