



# MACHINING CONDITIONS

GCTX 2002 NN LT 1000

T0002825

Material Group	SAPPHIRE TOOLS	Material Example	Hardness	Feed		Vc		Advised Feed [mm/t]	Advised Vc [m/min]
				min [mm/t]	max [mm/t]	min [m/min]	max [m/min]		
Steel	Non Alloyed	1	C35, Ck45, 1020, 1045, 1060, 28Mn6	125 HB	0.05	0.17	130	220	0.11
				190 HB	0.05	0.17	130	220	0.11
				250 HB	0.05	0.17	130	200	0.11
	Low Alloyed	2	42CrMo4, St50, Ck60, 4140, 4340, 100Cr6	230 HB	0.05	0.15	90	200	0.1
				280 HB	0.05	0.15	90	170	0.1
				180 HB	0.05	0.15	90	200	0.1
				350 HB	0.05	0.15	90	150	0.1
	High Alloyed	3	X40CrM0V5, H13, M42, D3, S6-5-2, 12Ni19	220 HB	0.05	0.14	60	170	0.1
				280 HB	0.05	0.14	60	150	0.1
				320 HB	0.05	0.13	60	130	0.09
				350 HB	0.05	0.12	60	100	0.09
Stainless Steel	Austentic	4	304, 316, X5CrNi18-9	180 HB	0.05	0.1	90	150	0.07
				240 HB	0.05	0.1	70	140	0.07
	Duplex	5	X2CrNiN23-4, S31500	290 HB	0.05	0.09	60	100	0.07
				310 HB	0.05	0.09	60	100	0.07
	Ferritic & Martensitic	6	410, X6Cr17, 17-4 PH, 430	200 HB	0.05	0.09	60	130	0.07
				42 HRc	0.05	0.08	50	90	0.07
Cast Iron	Grey	7	GG20, GG40, EN-GJL-250, N030B	150 HB	0.05	0.16	130	190	0.11
				200 HB	0.05	0.16	130	190	0.11
				250 HB	0.05	0.16	130	190	0.11
NTI Alloy	Fe, Ni & Co Based	8	GGG40, GGG70, 50005	150 HB	0.05	0.14	90	150	0.1
				200 HB	0.05	0.14	90	150	0.1
				250 HB	0.05	0.14	90	150	0.1
	Ti Based	9	Incoloy 800	240 HB	0.05	0.08	30	40	0.07
			Inconel 700	250 HB	0.05	0.08	30	40	0.07
Hardened Materials	Steel Chilled Cast Iron White Cast Iron	10	Stellite 21	350 HB	0.05	0.08	30	40	0.07
			T40	-	0.05	0.08	30	40	0.07
			TiAl6V4	-	0.05	0.08	40	60	0.07
			G-X300CrMo15	55 HRc	0.05	0.08	30	50	0.07
			Ni-Hard 2	400 HB	0.05	0.08	40	60	0.07
	X100CrMo13, 440C, G-X260NiCr42	11	45 HRc	0.05	0.11	50	90	0.08	70
			50 HRc	0.05	0.1	40	70	0.08	55
			55 HRc	0.05	0.09	30	60	0.07	45
Aluminum	Al (>8%Si)	12	AlSi12	130 HB	0.05	0.1	100	300	0.08