



MACHINING CONDITIONS

OFMT 05T305 TN LT 3000

M0002221

Material Group	SAPPHIRE TOOLS	Material Example	Hardness	D.O.C		Feed		Vc		Advised D.O.C [mm]	Advised Feed [mm/t]	Advised Vc [m/min]		
				min[mm]	max[mm]	min[mm/t]	max [mm/t]	min [m/min]	max [m/min]					
Steel	Non Alloyed	1	C35, Ck45, 1020, 1045, 1060, 28Mn6	125 HB	0.5	3.5	0.22	0.51	190	330	2.5	0.37	250	
				190 HB	0.5	3.5	0.22	0.51	190	300	2.5	0.37	220	
				250 HB	0.5	3.5	0.22	0.51	190	250	2.5	0.37	200	
	Low Alloyed	2	42CrMo4, St50, Ck60, 4140, 4340, 100Cr6	230 HB	0.5	3.5	0.18	0.4	150	210	2.5	0.32	180	
				280 HB	0.5	3.5	0.18	0.35	130	190	2.5	0.29	150	
				180 HB	0.5	3.5	0.18	0.4	150	240	2.5	0.32	200	
				350 HB	0.5	3.5	0.18	0.35	130	170	2.5	0.29	140	
	High Alloyed	3	X40CrMoV5, H13, M42, D3, S6-5-2, 12Ni19	220 HB	0.5	2.5	0.14	0.35	90	150	1.9	0.29	130	
				280 HB	0.5	2.5	0.14	0.35	90	130	1.9	0.29	120	
				320 HB	0.5	2.5	0.14	0.29	60	110	1.9	0.26	100	
				350 HB	0.5	2.5	0.14	0.29	60	90	1.9	0.26	80	
				180 HB	0.5	3.5	0.18	0.35	190	250	2.5	0.29	220	
Stainless Steel	Austentic	4	304, 316, X5CrNi18-9	240 HB	0.5	3.5	0.14	0.32	160	210	2.5	0.29	190	
				290 HB	0.5	2.5	0.14	0.29	70	130	1.9	0.26	100	
	Duplex	5	X2CrNiN23-4, S31500	310 HB	0.5	2.5	0.14	0.29	70	120	1.9	0.26	90	
Cast Iron	Ferritic & Martensitic	6	410, X6Cr17, 17-4 PH, 430	200 HB	0.5	3.5	0.18	0.35	150	210	2.5	0.29	190	
				42 HRc	0.5	2.5	0.18	0.32	90	150	1.9	0.26	130	
	Grey	7	GG20, GG40, EN-GJL-250, N030B	150 HB	0.5	3.5	0.22	0.51	150	240	2.5	0.37	200	
				200 HB	0.5	3.5	0.22	0.51	150	220	2.5	0.37	180	
				250 HB	0.5	3.5	0.22	0.51	150	190	2.5	0.37	160	
NITI Alloys	Fe, Ni & Co Based	8	GGG40, GGG70, 50005	150 HB	0.5	3.5	0.18	0.45	100	200	2.5	0.32	180	
				200 HB	0.5	3.5	0.18	0.45	100	180	2.5	0.32	150	
				250 HB	0.5	3.5	0.18	0.45	100	150	2.5	0.32	130	
	Ti Based	9	Incoloy 800	240 HB	0.5	2.5	0.14	0.29	30	50	1.9	0.26	32	
			Inconel 700	250 HB	0.5	2.5	0.14	0.29	30	50	1.9	0.26	30	
Hardened Materials	Steel Chilled Cast Iron White Cast Iron	10	Stellite 21	350 HB	0.5	2.5	0.14	0.29	30	50	1.9	0.26	30	
			T40	-	0.5	2.5	0.14	0.29	30	60	1.9	0.26	40	
			TiAl6V4	-	0.5	2.5	0.14	0.32	40	70	1.9	0.29	55	
			G-X300CrMo15	55 HRc	0.4	0.8	0.12	0.22	30	60	0.6	0.19	40	
	AI (>8%Si)	11	Ni-Hard 2	400 HB	0.4	1	0.12	0.29	40	80	0.9	0.22	50	
			45 HRc	0.4	1.3	0.12	0.29	40	80	1.1	0.22	60		
			X100CrMo13, 440C, G-X260NiCr42	50 HRc	0.4	1	0.12	0.26	40	70	0.9	0.21	55	
Aluminium			55 HRc	0.4	0.8	0.12	0.22	40	60	0.6	0.19	50		
			AlSi12	130 HB	0.5	3.5	0.22	0.51	200	400	2.5	0.4	280	