



# MACHINING CONDITIONS

SPMT 060304 TN LT 30

FM003100

Material Group	SAPPHIRE CUTTING TOOLS Group	Material Example	Hardness	D.O.C		Feed		Vc		Advised D.O.C	Advised Feed	Advised Vc	
				min[mm]	max[mm]	min[mm/t]	max[mm/t]	min[m/min]	max [m/min]	[mm]	[mm/t]	[m/min]	
Steel	Non Alloyed	1	C35, Ck45, 1020, 1045, 1060, 28Mn6	125 HB	0.3	6	0.06	0.12	190	330	2.4	0.1	
				190 HB	0.3	6	0.06	0.1	190	300	2.4	0.08	
				250 HB	0.3	6	0.06	0.1	190	250	2.4	0.08	
	Low Alloyed	2	42CrMo4, St50, Ck60, 4140, 4340, 100Cr6	230 HB	0.3	6	0.06	0.1	150	210	2.4	0.08	
				280 HB	0.3	6	0.05	0.1	130	190	2.4	0.08	
				180 HB	0.3	6	0.06	0.12	150	240	2.4	0.1	
				350 HB	0.3	6	0.05	0.1	130	170	2.4	0.08	
	High Alloyed	3	X40CrMoV5, H13, M42, D3, S6-5-2, 12Ni19	220 HB	0.3	6	0.06	0.08	90	150	1.8	0.07	
				280 HB	0.3	6	0.05	0.1	90	130	1.8	0.08	
				320 HB	0.3	6	0.05	0.08	60	110	1.8	0.06	
				350 HB	0.3	6	0.05	0.08	60	90	1.8	0.06	
Stainless Steel	Austenitic	4	304, 316, X5CrNi18-9	180 HB	0.3	6	0.06	0.08	190	250	2.4	0.07	
				240 HB	0.3	6	0.05	0.08	160	210	2.4	0.07	
	Duplex	5	X2CrNiN23-4, S31500	290 HB	0.3	6	0.05	0.08	70	130	1.8	0.07	
				310 HB	0.3	6	0.05	0.07	70	120	1.8	0.06	
	Ferritic & Martensitic	6	410, X6Cr17, 17-4 PH, 430	200 HB	0.3	6	0.05	0.08	150	210	2.4	0.07	
				42 HRc	0.3	6	0.05	0.07	90	150	1.8	0.06	
Cast Iron	Grey	7	GG20, GG40, EN-GJL-250, N030B	150 HB	0.3	6	0.05	0.14	150	240	2.4	0.12	
				200 HB	0.3	6	0.05	0.12	150	220	2.4	0.1	
				250 HB	0.3	6	0.05	0.12	150	190	2.4	0.1	
	Malleable & Nodular	8	GGG40, GGG70, 50005	150 HB	0.3	6	0.05	0.14	100	200	2.4	0.12	
				200 HB	0.3	6	0.05	0.12	100	180	2.4	0.1	
				250 HB	0.3	6	0.05	0.12	100	150	2.4	0.1	
NTI Alloys	Fe, Ni & Co Based	9	Incoloy 800	240 HB	0.3	6	0.04	0.08	30	50	1.8	0.06	
			Inconel 700	250 HB	0.3	6	0.04	0.08	30	50	1.8	0.06	
			Stellite 21	350 HB	0.3	6	0.04	0.08	30	50	1.8	0.06	
	Ti Based	10	T40	-	0.3	6	0.04	0.08	30	60	1.8	0.06	
			TiAl6V4	-	0.3	6	0.04	0.08	40	70	1.8	0.06	
Hardened Materials	Steel Chilled Cast Iron White Cast Iron	11	G-X300CrMo15	55 HRc	0.3	6	0.04	0.06	30	60	0.6	0.05	
			Ni-Hard 2	400 HB	0.3	6	0.04	0.06	40	80	0.9	0.05	
			45 HRc	0.3	6	0.04	0.1	40	80	1.2	0.08	60	
			50 HRc	0.3	6	0.04	0.08	40	70	0.9	0.06	55	
			55 HRc	0.3	6	0.04	0.06	40	60	0.6	0.05	50	
Aluminum	Al (>8%Si)	12	AlSi12	130 HB	0.3	6	0.08	0.14	200	400	2.4	0.12	280