

WNMG 080408 NX LT 1120M

T0004759

			 Group	Material Example	Hardness	D.O.C		Feed		Amax	Vc		Advised D.O.C	Advised Feed	Advised Vc
Material Group		min[mm]				max[mm]	min[mm/t]	max [mm/t]	[mm^2]	min [m/min]	max [m/min]	[mm]	[mm/t]	[m/min]	
Stainless Steel	Austentic	4	304, 316, X5CrNi18-9	180 HB	0.5	3.5	0.18	0.4	1.14	90	270	2.4	0.24	190	
				240 HB	0.5	3.5	0.18	0.4	0.95	80	220	2.4	0.21	170	
	Duplex	5	X2CrNiN23-4, S31500	290 HB	0.5	2.8	0.16	0.35	0.76	40	150	2	0.23	100	
				310 HB	0.5	2.8	0.16	0.35	0.76	40	140	2	0.23	90	
	Ferritic & Martensitic	6	410, X6Cr17, 17-4 PH, 430	200 HB	0.5	3.5	0.16	0.4	0.67	90	250	2	0.19	190	
				42 HRc	0.5	2.8	0.16	0.4	0.67	60	190	1.8	0.19	130	